



# Reliability Data Report

## Product Family R537

---

LTC6602 / LTC6603 / LTC6604

# Reliability Data Report

## Report Number: R537

Report generated on: Tue Oct 09 10:14:25 PDT 2012

OPERATING LIFE TEST					
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HRS (+125°C) <sup>1</sup>	No. of FAILURES <sub>2,3</sub>
QFN/DFN	75	0740	0740	75	0
Totals	75	-	-	75	0
PRESSURE COOKER TEST AT 15 PSIG , +121 DEG C					
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HRS	No. of FAILURES
QFN/DFN	50	1037	1037	1	0
Totals	50	-	-	1	0
TEMP CYCLE FROM -65 TO 150 DEG C					
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	No. of FAILURES
QFN/DFN	50	1037	1037	5	0
Totals	50	-	-	5	0
THERMAL SHOCK FROM -65 TO 150 DEG C					
PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	No. of FAILURES
QFN/DFN	50	1037	1037	5	0
Totals	50	-	-	5	0
<p>(1) Assumes Activation Energy = 0.7 Electron Volts  (2) Failure Rate Equivalent to +55 °C, 60% Confidence Level =24.44 FITS  (3) Mean Time Between Failure in Years = 4670.33  Note: 1 FIT = 1 Failure in One Billion Hours.  Note 2: HAST, Temp Cycle &amp; Thermal Shock are subjected to J-STD-020 Preconditioning</p>					