

RELIABILITY DATA

LT1675 / LT6555 / LT6556

8/21/2006

• OPERATING LIFE TEST

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HOURS ⁽¹⁾ AT +125°C	NUMBER OF ⁽²⁾ FAILURES
SSOP/TSSOP	144 144	9827	9901	144.35 144.35	0 0

• PRESSURE COOKER TEST AT 15 PSIG, +121°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE HOURS	NUMBER OF FAILURES
SSOP/TSSOP	50 50	9832	9832	12.00 12.00	0 0

• TEMP CYCLE FROM -65°C to +150°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	NUMBER OF FAILURES
SSOP/TSSOP	49 49	9832	9832	4.90 4.90	0 0

• THERMAL SHOCK FROM -65°C to +150°C

PACKAGE TYPE	SAMPLE SIZE	OLDEST DATE CODE	NEWEST DATE CODE	K DEVICE CYCLES	NUMBER OF FAILURES
SSOP/TSSOP	45 45	9832	9832	4.50 4.50	0 0

(1) Assumes Activation Energy = 1.0 Electron Volts

(2) Failure Rate Equivalent to +55°C, 60% Confidence Level = 12.74 FITS

(3) Mean Time Between Failures in Years = 8,954

Note: 1 FIT = 1 Failure in One Billion Hours.